



GLOSS@Guard

~Exterior Hi-Gloss Paint~

Product Index : 018

SANcora® GLOSS@Guard is a premium solvent-based high gloss paint, suitable for use on all types of wood and metal surfaces. It is a fungus-resistant high gloss architectural paint that is easy to apply and forms a smooth mirror-like tough paint film with excellent gloss and durability.

| | | |
|----------------------------|--|---|
| Usage | For decorative and protection of all types of interior and exterior wood and metal surfaces. It is also ideal for use as a marine enamel for topsides, deckhouse and engine rooms. | |
| Pack Size | 1 litre, 5 litres and 18 litres. | |
| Composition | Pigment | : Organic & Inorganic |
| | Binder | : Modified Alkyd |
| | Vehicle/Solvent | : White Spirit |
| Technical Data | Texture | : High Gloss Smooth Finish |
| | Theoretical Coverage | : Approx. 14- 16m ² / litre (Depending on surface evenness) |
| | Drying Time | : Single coat at standard thickness (28°C, 50% RH) |
| | | : Touch Dry ≤ 4 minutes |
| | | : Hard Dry ≤ 18 hours |
| | Recoating Time | : 10 hours |
| | Thinner/Cleaner | : White Spirit or Mineral Turpentine |
| Application | Brush/Roller | For normal use, thinning is not necessary. If required, add up to 10% by volume with White Spirit. |
| | Conventional Air Spray | Thin 10 - 20% by volume with White Spirit and adjust to requirement. |
| | Airless Spray | Ready for use. |
| Surface Preparation | Wood | : Wood must be dry and free from grease, dirt and other contaminants. Smoothen the surfaces with suitable grade sandpaper and dust off before application of paints. Surfaces must be dry and free from grease, dirt and other contaminants. Steel surfaces should be sanded or wire-brushed to remove mill scales and rust. For the best result, steel surfaces should be prepared by hand-powered tool according to BS7079 Part 1:1989 ST3 Standard |
| | Metal | : Surfaces should be cleaned and degreased. Apply with <i>SANcora</i> ® PROTECTIVE@Guard Etching Primer to ensure good adhesion. |
| | Galvanized / Aluminium | : Surfaces should be cleaned and degreased. Apply with <i>SANcora</i> ® PROTECTIVE@Guard Etching Primer to ensure good adhesion. |
| Shelf Life | 2 years at ambient temperature in unopened containers. | |

Paint Guide

| Surface Condition | Primer - To Paint One Coat | Undercoat - To Paint One Coat | Finishing - To Paint Two Coats |
|----------------------------------|--|----------------------------------|--------------------------------|
| Wood Surfaces | <i>SANcora</i> ® SILVER@Guard | <i>SANcora</i> ® UNDERCOAT@Guard | <i>SANcora</i> ® GLOSS@Guard |
| Metal Surfaces | <i>SANcora</i> ® RUST@Guard | <i>SANcora</i> ® UNDERCOAT@Guard | <i>SANcora</i> ® GLOSS@Guard |
| Galvanized or Aluminium Surfaces | <i>SANcora</i> ® PROTECTIVE@Guard Etching Primer | <i>SANcora</i> ® UNDERCOAT@Guard | <i>SANcora</i> ® GLOSS@Guard |

Safety, Health and Environmental Information

When applying paint, it is advisable to wear eye protection and suitable gloves.

In case of contact with eye, rinse with plenty of water immediately and seek medical advice.

Remove splashes of paint from skin by using soap or water.

Keep container tightly closed and away from food, drinks, animal feed and out of the reach of children.

Ensure good ventilation during application and drying.

Paint must always be stored in upright position and a cool place.

Dispose off any paint waste in accordance with the appropriate Environmental Quality Regulations.

Refer to Material Safety Data Sheet for complete product safety information.

The above information is given to the best of our knowledge based on our existing laboratory test and practical experience, however since conditions of actual use are beyond our control any recommendations and suggestions are made without warranty, express or implied and we reserve the right to alter the given data without prior notice.

SYARIKAT SANLAND PAINT INDUSTRIES SDN BHD (19733-T)

Plot 52 & 53, Lorong Kilang 15, Tupai Light Industrial Area, 34000 Taiping, Perak Darul Ridzuan, Malaysia.

Tel : 605-8068777 Fax : 605-8074955